

# DCMT.UR 32.51 Z12



## APPLICATION

- Suitable for fine to heavy machining of steels

- Continuous and interrupted cut



## GRADE Z12

This grade is a MT-CVD coated functionally graded WC-Co carbide within ISO range P05-P25, for fine to heavy machining of steels

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P05 - P25		K05 - K25			
Sfm ft/min	525 - 673		492 - 623			
Fn Inch/rev	.006 - .008		.006 - .008			
ap Inch	.016 - .079		.016 - .079			

### LEGEND

Sfm (Vc)	Surface Feet per Minute
Fn (ipr)	Feed per revolution
Fz (ipt)	Feed per tooth
ap	Depth of cut

### FORMULA

$S \text{ (RPM)} = \text{Sfm} * 12 / \pi / D = \text{rev per minute}$
$F \text{ (IPR, inch per revolution)} = S * \text{Fn} = \text{feed per minute}$
$F \text{ (IPM, inch per minute)} = S * Fz * n.\text{flutes} = \text{feed per minute}$
$\text{Sfm} = S * D * \pi / 12$

**TURNING CARBIDE INSERT**