DCMT.UR 32.52 Z12

APPLICATION

- Suitable for fine to heavy machining of steels

- Continuos and interupted cut

GRADE Z12

This grade is a MT-CVD coated functionally graded WC-Co carbide within ISO range P05-P25, for fine to heavy machining of steels

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P05 - P25		K05 - K25			
Sfm ft/min	459 - 787		427 - 738			
Fn Inch/rev	.006016		.006016			
ap Inch	.031079		.031079			

LEGEND				
Sfm (Vc)	Surface Feet per Minute			
Fn (ipr)	Feed per revolution			
Fz (ipt)	Feed per tooth			
Sfm (Vc) Fn (ipr) Fz (ipt) ap	Depth of cut			

FORMULA

S (RPM) = Sfm * 12 / π / D = rev per minute F (IPR, inch per revolution) = S * Fn= feed per minute F (IPM, inch per minute) = S * Fz * n.flutes= feed per minute Sfm = S * D * π / 12

TURNING CARBIDE INSERT

