

RCMT.UR 10T3MOE Z9



APPLICATION

- Suitable for fine to heavy machining of steels and stainless-steels
- Continuous and interrupted cut



GRADE Z9

This grade is a MT-CVD coated functionally graded WC-Co carbide within ISO ranges P15-P35 and M10-M30, for fine to heavy machining of steels and stainless-steels

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P15 - P35	M10 - M30	K15 -K35			
Sfm ft/min	525 - 1083	312 - 640	492 - 1017			
Fn Inch/rev	.006 - .024	.007 - .021	.006 - .024			
ap Inch	.016 - .157	.016 - .157	.016 - .157			

LEGEND

Sfm (Vc)	Surface Feet per Minute
Fn (ipr)	Feed per revolution
Fz (ipt)	Feed per tooth
ap	Depth of cut

FORMULA

S (RPM) = Sfm * 12 / π / D = rev per minute
F (IPR, inch per revolution) = S * Fn= feed per minute
F (IPM, inch per minute) = S * Fz * n.flutes= feed per minute
Sfm = S * D * π / 12

TURNING CARBIDE INSERT