




SCMT.UR 32.52 Z5P

APPLICATION

- Suitable for fine to heavy machining of steels
- Continuous and interrupted cut



GRADE Z5P

This grade is a PVD coated fine grained WC-Co carbide within ISO range P25-P40, for fine to heavy machining of steels

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P25 - P40	M25 - M40	K25 -K40			
Sfm ft/min	410 - 935	213 - 509	328 - 755			
Fn Inch/rev	.003 - .017	.004 - .016	.003 - .017			
ap Inch	.031 - .118	.031 - .118	.031 - .118			

LEGEND

Sfm (Vc)	Surface Feet per Minute
Fn (ipr)	Feed per revolution
Fz (ipt)	Feed per tooth
ap	Depth of cut

FORMULA

S (RPM) = Sfm * 12 / π / D = rev per minute
F (IPR, inch per revolution) = S * Fn= feed per minute
F (IPM, inch per minute) = S * Fz * n.flutes= feed per minute
Sfm = S * D * π / 12

TURNING CARBIDE INSERT