



TPMR .47 222 Z7



APPLICATION

- Single-sided positive turning insert with chipbreaker
- Suggested to use on manual lather for machining of steels

GRADE Z7

This is a a MT-CVD coated functionally graded WC-Co carbide within ISO range P20-P45, for fine to medium machining of steels

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P30	M30				
Sfm ft/min	328 - 574	197 - 344				
Fn Inch/Z	0.0059 - 0.0157	0.0065 - 0.0142				
ap Inch	0.031 - 0.157	0.031 - 0.157				

LEGEND

Sfm (Vc)	Surface Feet per Minute
Fn (ipr)	Feed per revolution
Fz (ipt)	Feed per tooth
ap	Depth of cut

FORMULA

$S \text{ (RPM)} = Sfm * 12 / \pi / D = \text{rev per minute}$
$F \text{ (IPR, inch per revolution)} = S * Fn = \text{feed per minute}$
$F \text{ (IPM, inch per minute)} = S * Fz * n.\text{flutes} = \text{feed per minute}$
$Sfm = S * D * \pi / 12$