



CNMG.FM 321 Z9

APPLICATION

- Suitable for fine to medium machining of steels and stainless-steels
- Continuous and interrupted cut



GRADE Z9

This grade is a MT-CVD coated functionally graded WC-Co carbide within ISO ranges P15-P35 and M10-M30, for fine to medium machining of steels and stainless-steels

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P25	M25	K20		S20	
Sfm ft/min	656 - 935	394 - 558	623 - 886		115 - 246	
Fn Inch/rev	.006 - .010	.006 - .009	.006-.010		.006 - .008	
ap Inch	.020 - .118	.020 - .118	.020 - .118		.020 - .094	

LEGEND

Sfm (Vc)	Surface Feet per Minute
Fn (ipr)	Feed per revolution
Fz (ipt)	Feed per tooth
ap	Depth of cut

FORMULA

S (RPM)	$= Sfm * 12 / \pi / D = \text{rev per minute}$
F (IPR, inch per revolution)	$= S * Fn = \text{feed per minute}$
F (IPM, inch per minute)	$= S * Fz * n.\text{flutes} = \text{feed per minute}$
Sfm	$= S * D * \pi / 12$

TURNING CARBIDE INSERT