DNGA 432 T7 ZCC

APPLICATION

- General machining for hardened steel and cast iron
- Better using dry, no coolant
- Suggested to continuos cutting condition.

GRADE ZCC

Grade ZCC in its outstanding wear resistance and thermal shock resistance with high speed cutting. Pure raw materials give stability and fine microstructure to the products.

Through HIP process, shaped bodies are completely condensed so that finished goods are strong and resistant against fracture and wear. Excellent wear resistance. Al 2O3 +TiC(N).





	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP			K10			H10
Sfm ft/min			98 - 328			98 - 492
Fn Inch/rev			.003008			.002013
ap Inch			.004012			.004012

LEGEND

Sfm (Vc)	Surface Feet per Minute	
Sfm (Vc) Fn (ipr) Fz (ipt)	Feed per revolution	
Fz (ipt)	Feed per tooth	
ар	Depth of cut	

FORMULA

S (RPM) = Sfm * 12 / π / D = rev per minute F (IPR, inch per minute) = S * Fn= feed per minute F (IPM, inch per minute) = S * Fz * n.flutes= feed per minute Sfm = S * D * π / 12