


# WNMG.R 432 Z11



## APPLICATION

- Suitable for medium to heavy machining of cast-irons
- Continuous and interrupted cut



## GRADE Z11

This grade is a MT-CVD coated WC-Co carbide within ISO range K10-K25, for medium to heavy machining of cast-irons

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P10 - P25		K10 - K25			H10 - H25
Sfm ft/min	623 - 902		591 - 853			115 - 180
Fn Inch/rev	.010 - .021		.010 - .021			.005 - .010
ap Inch	.079 - .22		.079 - .22			.016 - .039

### LEGEND

Sfm (Vc)	Surface Feet per Minute
Fn (ipr)	Feed per revolution
Fz (ipt)	Feed per tooth
ap	Depth of cut

### FORMULA

$S \text{ (RPM)} = \text{Sfm} * 12 / \pi / D = \text{rev per minute}$
$F \text{ (IPR, inch per revolution)} = S * \text{Fn} = \text{feed per minute}$
$F \text{ (IPM, inch per minute)} = S * Fz * n.\text{flutes} = \text{feed per minute}$
$\text{Sfm} = S * D * \pi / 12$

**TURNING CARBIDE INSERT**