

SNHX 11023 Z6P

APPLICATION

- Double-sided disc milling insert
- Thickness .091" for cutters 938...4mm



GRADE Z6P

This is a TIN PVD coated fine grained WC-Co carbide within ISO-grade range P25-P50 for machining of steel and stainless steel with disc mills 938

	STEEL	STAINLESS	CAST IRON	NON FERROUS	S.ALLOYS	HEAT TREATED
GROUP	P30	M30	K30			
Sfm ft/min	935 - 1394	558 - 837	886 - 1312			
Fz Inch/Z	0.0039 - 0.0157	0.0043 - 0.0142	0.0039 - 0.0157			
ap Inch						

LEGEND

Sfm (Vc) Fn (ipr) Fz (ipt) ap	Surface Feet per Minute
Fn (ipr)	Feed per revolution
Fz (ipt)	Feed per tooth
ар	Depth of cut

FORMULA

S (RPM) = Sfm * 12 / π / D = rev per minute F (IPR, inch per revolution) = S * Fn= feed per minute F (IPM, inch per minute) = S * Fz * n.flutes= feed per minute Sfm = S * D * π / 12